

TRANS-WRAP™

CARBON FIBER PIPELINE REPAIR SYSTEM

Description Trans-Wrap™ is a bidirectional non-woven 100% carbon fiber composite, saturated with NRI's proprietary epoxy system, Thermo-Poxy™. The Trans-Wrap carbon fiber is oriented in the 0° / 90° directions and is stitched resulting in outstanding tensile values in both directions. It has a high thickness per layer resulting in fewer layers needed for reinforcement and quicker applications. The Thermo-Poxy Epoxy system is a two-part, 100% solid epoxy designed for use in a wide variety of environments possessing excellent chemical resistance and high temperature ratings.

Mechanical Properties	Test	Method	Result
	Tensile Strength	ASTM D3039	Hoop: 130,000 psi (8,963.18 bar) Axial: 130,000 psi (8,963.18 bar)
	Elongation @ Break	ASTM D3039	1.46%
	Tensile Modulus	ASTM D3039	7,144,000 psi (492,561.5 bar)
	Laminate Thickness	Per layer	0.035" (0.889 mm)
	Hardness, Shore D @ 75°F (24°C)	ASTM D2240	85
	Syntho-Subsea™ LV Primer Epoxy Mechanical Properties		
Tensile Strength	ASTM D3039	6,000 psi (413.68 bar)	
Compression Strength	ASTM D695	7,380 psi (508.83 bar)	
Flexural Strength	ASTM D790	4,550 psi (313.71 bar)	
Flexural Modulus	ASTM D790	142,188 psi (9803.51 bar)	
Lap Shear Strength	ASTM D3163	1,782 psi (122.86 bar)	
Abrasion Resistance	CS17 wheels with 1,000 gram weights	34.0 mg/1,000 cycles	

- Typical Applications**
- Pipeline Repair
 - Containment and shear reinforcement
 - Bridge column repair
 - Pile repair

- Benefits**
- Long working time even in hot environments
 - High temperature rating with an ambient cured epoxy
 - Thick laminate for cost effective installation
 - Applicable in damp and wet environments
 - High strength and light weight
 - Manufactured in ISO 9001 certified facility
 - Full factory engineering calculations, consultation, and support ensuring safe and successful repairs



TRANS-WRAP™

CARBON FIBER PIPELINE REPAIR SYSTEM

TRANS-WRAP™
CARBON FIBER PIPELINE REPAIR SYSTEM

Physical Properties	Property	Typical Test Value
	VOCs:	None
	Pot Life:	75 Minutes at 75°F (24°C)
	Working Time:	45 Minutes at 75°F (24°C)
	Gel Time:	Approx. 161 Minutes at 75°F (24°C)
	Set Time:	4 Hours at 75°F (24°C)
	Resin Application:	Field mixed and saturated
	Service Temperature:	-50° to 250°F (-45° to 121°C)
	Shelf Life:	12 Months with recommended storage conditions

Warranty

©Neptune Research Inc. (NRI) NRI® is a registered trademark while Trans-Wrap™, Thermo-Poxy™, and Syntho-Subsea LV™ are trademarks of NRI. NRI utilizes a process of continuous product improvement for all of our products. While we do strictly adhere to our products' specifications, we routinely implement product improvements. Therefore, please contact your local NRI distributor or office for the most current product specifications. NRI warrants the quality of this product when used according to directions. Trans-Wrap is NOT an approved coating system. Failing to coat per standard procedures can lead to atmospheric corrosion damage. Apply protective coatings per company standards. User shall determine suitability of product for use and assumes all risk. The seller will not accept liability for more than product replacement. TNSW DS 0214